

LEDTECH ELECTRONICS CORP.

NANYA ROAD, MUGANG ZHAOQING CITY GUANGDONG CHINA.

TEL:86-758-2875541,2870651,2877464,2876185,2877017

FAX:86-758-2878014

Http://www.ledtech.com.tw

## **SPECIFICATION**

PART NO.: LT3321-81-UAC2

10.0MM ROUND LED LAMP



Approved by	Checked by	Prepared by
San	Spring	ChunXiu




Page: 1/7

#### **Description**

This Bluish Green lamps are made with InGaN/Sapphire chips and Green Diffused epoxy resin.

## Package Dimensions



1.All dimensions are in millimeters.

2. Tolerance is £0.25mm unless otherwise noted.

Part No.	LED	Chip	Lens Color
Pait No.	Material	Emitting Color	Lens Color
LT3321-81-UAC2	InGaN/Sapphire	Bluish Green	Green Diffused

First Edition Date: 2005/05/18



### **Absolute Maximum Ratings at Ta=25**

Parameter	Symbol	Rating	Unit
Power Dissipation	Pd	120	mW
Reverse Voltage	Vr	5	V
D.C. Forward Current	If	30	mA
Reverse (Leakage) Current	Ir	50	μA
Peak Current (1/10 Duty Cycle , 0.1 ms Pulse Width)	If(Peak)	100	mA
Operating Temperature Range	Topr	-25 to +85	
Storage Temperature Range	Tstg	-40 to +100	
Lead Soldering Temp.(1.6mm from body) for 5 seconds	260		
Electrostatic discharge (ESD)	300	V	

### **Electrical and Optical Characteristics:**

Parameter	Symbol	Condition	Min.	Тур.	Max.	Unit
<b>Luminous Intensity</b>	Iv	If=20mA	1000	1900		mcd
Forward Voltage	Vf	If=20mA		3.2	4.0	V
Dominant Wavelength	D	If=20mA		500		nm
Reverse Current	Ir	Vr=5V			50	μ <b>A</b>
Viewing Angle	2 1/2	If=20mA		34		deg
Spectrum Line Halfwidth		If=20mA		35		nm


NOTE: THE DATAS TESTED BY IS TESTER

First Edition Date: 2005/05/18


Page: 2/7



### **Typical Electrical / Optical Characteristics Curves:**




FORWARD CURRENT VS.APPLIED VOLTAGE




Page: 3/7

FORWARD CURRENT VS. LUMINOUS INTENSITY



AMBIENT TEMPERATURE VS. FORWARD CURRENT



RADIATION DIAGRAM

First Edition Date: 2005/05/18



#### **Reliability Test**

NO.	Discription	Test Method	Test Condition
1	Operational life	1000 Hrs	IF=20mA, Ta=25 ℃
2	High Temp. Storage	1000 Hrs	100 €
3	Low Temp. Storage	1000 Hrs	-40 C
4	High Temp./High Humidity	1000 Hrs	60 €, 95%
5	Temperature Cycling	100 Cycles	-30 C(30min) → +25 C(5min) → +80 C(30min) → +25 C(5min)
6	Damp Heat Cyclic	40 Cycles Time of 1 cucle: 6 hrs	IF=20mA, Ta=25 € -0 € £(2H) 65 € £2 90-95 %RH(3H) -0 € £(1H)
7	Soldering Heat	5 Sec.	260±5°C 1.6mm from bottom of case
8	Solderability	5±0.2 Sec. Wave soldering.	260±5°C Speed of immersing and lifting 25±2.5mm/sec
9	Drop	X.Y.Z Direction each 1 time	Maple plate, 75cm
10	Lead pull	10 Sec.	Weight 0.5Kg
11	Lead Bend	2 times	Weight 0.25Kg,Bending Angle=90 °

The result of the above Reliability test will be referred to the Electrical and Optical Characteristic in this Specification and Judgment will be made in accordance with the following criteria listed below.

### Reliability Test Failure Judgment Criteria

Item	Criteria for Judgment
Foward Voltage	More than 120% X upper limit of spec.
Reverse (Leakage) Current	More than 100% X upper limit of spec.
Luminous Intensity	More than 50% X Lower limit of spec.
Solderbility	Less than 95 %

First Edition Date: 2005/05/18

Page: 4/7



#### **Precautions:**

TAKE NOTE OF THE FOLLOWING IN USE OF LED

#### 1. Temperature in use

Since the light generated inside the LED needs to be emitted to outside efficiently, a resin with high light transparency is used; therefore, additives to improve the heat resistance or moisture resistance (silica gel, etc) which are used for semiconductor products such as transistors cannot be added to the resin.

Consequently, the heat resistant ability of the resin used for LED is usually low; therefore, please be careful on the following during use.

Avoid applying external force, stress, and excessive vibration to the resins and terminals at high temperature. The glass transition temperature of epoxy resin used for the LED is approximately 120-130 °C.

At a temperature exceeding this limit, the coefficient of liner expansion of the resin doubles or more compared to that at normal temperature and the resin is softened.

If external force or stress is applied at that time, it may cause a wire rupture.

#### 2. Soldering

Please be careful on the following at soldering.

After soldering, avoided applying external force, stress, and excessive vibration until the products go to cooling process (normal temperature), <Same for products with terminal leads>

- (1) Soldering measurements:
  - Distance between melted solder side to bottom of resin shall be 1.6mm or longer.
- (2) Solder dip: Preheat: 90 °C max. (Backside of PCB), Within 120 seconds Solder bath: 250 °C max. (Solder temperature), Within 5 seconds
- (3) Soldering iron: 250 °C max. (Temperature of soldering iron tip), Within 3 seconds

#### 3. <u>Insertion</u>

Pitch of the LED leads and pitch of mounting holes need to be same

#### 4. Others

Since the heat resistant ability of the LED resin is low, SMD components are used on the same PCB, please mount the LED after adhesive baking process for SMD components. In case adhesive baking is done after LED lamp insertion due to a production process reason, make sure not to apply external force, stress, and excessive vibration to the LED and follow the conditions below.

Baking temperature: 120 °C max. Baking time: Within 60 seconds

If soldering is done sequentially after the adhesive baking, please perform the soldering after cooling down the LED to normal temperature.


First Edition Date: 2005/05/18

Page: 5/7



**Page: 6/7** 





First Edition Date: 2005/05/18



### **COMPONENT AND MATERIALS:**

ITEM		MATERIALS	
CUSTOMER PART NO.			
LEDTECH PART NO.		LT3321-81-UAC2	
LED CHIP		InGaN ON Sapphire	
LEADFRAME		Iron covered with Silver	
A	ADHESIVE	SILVER FILLED EPOXY	
EPOXY RESIN	RESIN	EPOXY	
	HARDENNER	EPOXY	
	DIFFUSANT	EPOXY	
	COLORING DYE	EPOXY	
BONDING WIRE		GOLD	

First Edition Date: 2005/05/18

Page: 7/8